



Rapid Lion PU Windshield Adhesive

1 – DESCRIPTION

Rapid Lion PU Windshield Adhesive is a component, moisture curing polyurethane based adhesive for direct glazing in Automotive Glass Replacement.

2 – PROPERTIES

- One component formulation
- Good non-sag properties
- Short cut-off string
- Cold application
- Fast curing – Rapid strength development
- High mechanical performance
- High Modulus
- High initial bond strength
- Can be overpainted

3 - APPLICATIONS

It is especially useful in bonding windshield glass into automotive frames

4 - INSTRUCTIONS

- Remove the damaged glass. Before application ensure that surfaces are clean, dry and free from dust and grease.
- Shake the Polyurethane Windshield Adhesive Primer for at least 30 seconds (after hearing the ball move) before application.
- Apply Windshield Adhesive Primer to the outer edge of the glass where the urethane bond will be made and allow to dry.
- Ensure that primer is tack-free dry before proceeding.
- Cut tip of the nozzle to desired shape and size to provide a bead height sufficient to give good contact with the windshield around the entire perimeter. A triangular shaped notch will provide the optimal bead shape and height.
- It is recommended to apply the adhesive with a pneumatic sealant gun.
- Apply Polyurethane Windshield Adhesive directly to the glass
- Position the glass by aligning the masking tape on glass and car body. Press glass in place to assure complete contact with the Polyurethane Windshield Adhesive



5- STORAGE AND SHELF LIFE

9 months if stored properly in its original package between +5 °C and 30 °C.

6- PACKAGING

Product	Weight	Package
Black	300ml	12

7- RESTRICTIONS

- Avoid application below 5 °C and above 40 °C.
- Do not apply on frozen or wet surfaces or through standing water.

8- TECHNICAL PROPERTIES

BEFORE CURING	
Basis	: Polyurethane
Consistency	: Thixotropic
Curing Mechanism	: Moisture Curing
Density	: 1,13±0,03 g/ml
Tack free time	: 30±10 min. (23°C and 50% R.H)
Curing Rate	: Min. 3,5 mm/day (23°C and 50% R.H)
Sagging	: 0 mm (EN ISO 7390)

AFTER CURING	
Hardness Shore A	: 55-60 After 28 days
Paintability	: Yes *
Elongation at break	: Min. 300% (ASTM D412)
Tensile Strength	: Min. 4 N/mm ² (ASTM D412)

*Considering the diversity of paint base and quality, compatibility tests should be done before application.